

Cordones - Cables de Acero - Cincados

Formación 1 x 7			
Código	Ø Nominal (mm)	Sección (mm ²)	σ Rotura (daN)
MN-100b	4.80	14.07	1.636
MN-100	6.00	21.98	2.555
MN-100a	7.50	34.37	3.996
-----	8.10	40.00	4.657
MN-101	9.00	49.49	5.753
-----	10.50	67.35	7.329
-----	12.00	87.96	10.225

Formación 1 x 19			
Código	Ø Nominal (mm)	Sección (mm ²)	σ Rotura (daN)
-----	6.30	23.37	2.629
-----	7.50	33.63	3.783
MN-101b	9.00	48.26	5.429
MN-101a	10.50	65.74	7.396
-----	12.50	93.29	10.495
-----	14.50	117.04	13.167
-----	16.00	152.73	17.182

Según Norma IRAM 722